
COATING METHOD FOR PAPER AND DEVICE THEREFOR



(19)日本国特許庁 (JP)

(12) 公開特許公報(A)

(11)特許出願公開番号 特別2000-107666 (P2000-107666A)

(43)公開日 平成12年4月18日(2000.4.18)

(51) Int.Cl.7		微別記号	FΙ			<u>5</u>	73-1*(参考)
B 0 5 C	1/08		B05C	1/08			
B05D	1/28		B05D	1/28		4 F 0 4 0	
	5/02			5/02		4	L055
	7/00			7/00		F	
D21H	23/34		D21H 2	. H 23/34			
			審查請求	未請求	請求項の数2	OL	(全 5 頁)
(21)出顧番号		特願平10-285232	(71) 出額人	000183484			
			日本製紙株式会社				
(22) 出顧日		平成10年10月7日(1998.10.7)		東京都	比区王子1丁目	4番1号	}
			(72)発明者 佐藤 友治				
				山口県岩国市飯田町2 丁目8番1号 日本			
				製紙株式	製紙株式会社岩国工場内		
			(72)発明者	音羽 推	音羽 徽		
				山口県岩国市飯田町2 丁目8番1号 日本			
				製紙株式	大会社岩国工場	4	
			(74)代理人 100074572				
				弁理士	河澄 和夫		

最終頁に続く


(54) 【発明の名称】 紙の塗工方法とその装置

(57)【要約】 (修正有)

【課題】 高速プレードコーターにおける断紙の発生類 度を減少させる。

【解決手段】 ブレードコーターのバッキングロールR の鏡面又は紙が接触しない外周曲面の何れか一方又は両 方に、微細な水ミストを噴霧する。

【効果】 断紙原図の化シンに、飛散した塗工液ミスト がバッキングロールの鏡面には紙が強地しない外間曲面 で乾燥原化して単に液的とかった。 キカが毛浜面に表し し、新紙を発生させることが認められる。 本発明は、微 棚な水ミストを興寒することにより、塗工液粧の発生を 勝つ、新紙発生を被かさせる。



【特許請求の範囲】

【請求項1】 強工液を建工された紙の裏面をバッキングロールに当接させながら独工面にアレードを押し当て 定金工量を調整る紙の建工方法において、バッキング ロールの両端部接面又は外用曲面で紙と接触とない部分 のいずれか一方又は両方に、ザウター平均配径が100 瓜m~400μmの範囲から選択された平均部径の水ミ スト・収集することを特徴とする紙が施工方法。

【請求項2】 塗工液を塗工された紙の裏面をバッキングロールに当接させながら塩工面にアレードを押し当て で金工量を調整さ紙の塗工装置において、バッキング ロールの両端部接面又は外周曲面で紙と接触とない部分 のいずれか一方又は両方にずウター平均粒径が100μ m~400μmの水ミストを鳴霧できる噴霧装置を備え たことを特徴とする紙の塗工装置。

【発明の詳細な説明】

[0001]

【発明の属する技術分野】本発明は、ブレードコーター で紙に途工液を竣工する工程において、紙切れ発生が少 なく、高速採業性、生産効率に優れたブレード途工方 法、塗工装置に関するものである。 [0002]

【栄素の技術】近年オフセット印刷用紙は、チラシ、カ タログ、パンフレット、ダイレクトメール等広告、宣伝 を目的とした商業印刷分野での需要が着実に伸げている ことが特徴である。これ・6商業印刷物は、それ自体の商 品価値は続いが、宣伝媒体として目的が達成されること が重要であるので、低コストで印刷仕上がりの供した が成められてきている。印刷仕上がりを向上させるため には、紙の平滑性を向上させるとともに、印刷インクの 映み込みやにしたを少なくするを受がある。

(2003) 括表面に、顔料と含成態能等により薄い弦皮膜 を形成した途工紙は、上配目的のために製造され、商業 用印刷分野において、最も多く用いられている。また、 その一方でユーザーのコストダウン指向も一層強まって きており、使用する紙も低クレード化、軽量化に向かっ ている。

【0004】このような旺盛な軽量堂工脈の需要に対応するため、紙メーカーでは製品のより効率的な生産とコストゲウンを図るべく、塗主環側のが風、高速化を患かている。このような状況下で高品質を維持したまま生産性を上げることが重要な技術が課題であり、強工方式の検、強工の必要は、塗主添りでは、全が多りてもる「他のでランでが、全のでランでない。というでは、対域と強工を施して行うオフマシン方式と、一台のマシンでが低したがあり、オンマシン後工方式があり、オンマシン後工方式の方がより効率的な生産が可能である。また、原紙に安価を類相と含む下途り塗工液をオンマシンで強工力で後、上途、原紙の実施を含む下途り塗工液をオンシンで強工力で後、上途、上端りを加まるととにより、品質的には下途り強工液を他工することにより、品質的には下途り強工法を他工することにより、品質的には下途り強工法とり原紙の被関性が向上

し、面状や印刷品質も良くなることから、軽量塗工紙の 製造においても多層塗工化が進む傾向にある。

【0005】オンマシン億工には、主として、ブレードコーターが用いられる。プレードコーターは、主として、ロールアプリケート方式とファウンテンアプリケート方式がある。ロールアリケート方式は、図2に示すように、アプリケーターロールにより強工された紙の裏両を、アプリケーターロールにより強工された紙の裏両をプレードを押し当てて塗工量を調整する竣工方式であり、ファウンデンアプリケート方式は、図3に示すごと、バッキングロールに当接して走行する紙の表面に、ノズルから塗工液を噴出させて紙表面に塗工液を修工するとともに、塗工面にプレードを押し当てて竣工量を調整する差と方式である。

【0007】しかし、オンマシンで第工する場合、控紙から 上塗り第工、乾燥まで装置の長さが呼飛に長くなるた か、一度紙切れ、断紙が が発生した場合。通紙に直すた めに時間がかかり、生産効率が大きく低下する。そのた め、出水る限り階紙の発生頻度を減らすための製造技術 確立が必要となる。

【0008】コーターでの断転には、紙に過失なテンションが加わった場合以外にも、覆々の更因が考えられる。例 えば、建工後ミストが飛散し、建工ペッド・建工ペットの 周辺、パッキングロールの外周曲面及び阿端部の円形側 面である鏡面、周辺機器等に付着し、更に乾燥して固化 たち金銭面、周辺機器等に付着し、更に乾燥して固化 たり、原料粕や汚れ、チリ・異物混入等に由来する原紙 欠陥要因な増速によるドローやテンションの交動等機械 的変更収むし続い発生する。

【0009】このように数多くの断紙要因を減らすために、 提業現場では緑心の注意を払っており、マシン停止時に 毎所入金に洗浄を行って対応している。またコーサーで の金工液ミストの滑散を最小限にするために、バッキン グロール上部や入口・出口・塗工液/シストリファントでは、ファウンテンアリットでは、 ルシートを張ったり、ファウンテンアリットのリッフ両サイドに飛散助止用のゴム・トや塩と板、テープ等を取り 作行なると様々の工夫もをされている。

【0010】 にもかかわらず、特にオンマシンブレードコー ターで報量の塗工紙を高速で製造する場合には、断紙発 生頻度が高くなり、一度断能が発生したら生産ロスが大 さく、道紙に費やす時間ロスも増加し、生産効率を大き く低下させるという問題がある。 [0011]

【発明が解決しようとする課題】以上のような状況に鑑み、本発明の課題は断紙発生が少なく、生産効率に優れ 本プレード塗工方法とその塗工装置を提供することにある。

[0012]

【課題を解決するための手段】断紙は、紙の強度以上の

テンションがかかることが主たる原因であるが、図3に 示す塗工装置の一例であるファウンテンアプリケート方 式のブレードコーターについて、断紙の原因を鋭意追求 したところ、塗工液ミストが飛散し、塗工ヘッド、塗工 液パン周辺、バッキングロール、鏡面等に付着し、更に 乾燥し生成した塗工液粕が紙面に飛散、落下し、欠陥の 核となって断紙が発生する場合も多々あることが判明し た。ファウンテンのノズルから噴射された塗工液は、図 1において、紙のエッジから約5~10mmのドライエ ッジ部分dを除く部分に向けて噴射されるが、紙のドラ イエッジ部分d及び紙と接触しないバッキングロールR 両端の外周曲面部分Nにも飛散する。また、更に、バッ キングロールRの両端の鏡面Mにも飛散する。ドライエ ッジ部分d及びバッキングロール両端の外周曲面部分で 紙と接触していない部分Nに飛散した塗工液ミストは、 ブレードBにより掻き落とされるので、塗工液粕はそれ 程大量には蓄積しない。ところが、バッキングロールの 鏡面Mに飛散した塗工液は徐々に蓄積し、乾燥固化し、 塗工液粕塗となりやすい。

[0033] 彼って、本発明では、図1に示す位置に設置した噴霧装置を用いて、バッキングロールRの鏡面Mに 砂線和な水ミストを連続的に噴霧し、粕を乾燥をせないこ とにより、断紙の発生頻度を大幅に減少させることがで きた、さらに、バッキングロールRの両端の外周曲面部 ケボ青粉毛を接触していない能分形しも塗工液の粒が発 生することがあるので、この部分にも微細なホミストを 噴霧すると、さらに、断筋の発生頻度を減少させる効果 が大きいことが即同した。

[0014] 以下、本界肥か特徴を評述する。本発明者は、 断紙の風区を観覧追求したとろ、主にバッキングロー ル両縁の傾面に付着した強正液ミストが乾燥して生した 遠工液粕が、バッキングロールの回転による適心力や、 紙の走行により発生する気流により、飛散して低面に落 下場し、それが核となって断紙が発生しているケー スが比較的多いことを認めた。

【0015】よって、バッキングロール両端の鏡面に付着した塗工液ミストを連続的に洗い流し、塗工液的の形成を 防止するために、パッキングロール両端の鏡面及に水シャワーを連続的に流す方法を試みたが、断紙発生頻度は さほど減少しなかった。

【0016】そこで、断紙要因を東に締結に再調整した結果、 乗、鎮面に付着した塗工液ミストを常時温源状態にして おくことが定域料の深酸防止に効果があり、断極発生類 度を減らすことができることを認めた。温源状態を保持 させる方法についても検討した結果、水シャワーではな く、高圧空気を用いて水の粒径を小さてきる気水混合 ミストの方が効果が大きいことを認めた。

【0017】この理由は明確ではないが、より微細な水ミストの方が、付着した塗工液ミストあるいは塗工液粕に対してより均一に水分が浸透し、湿潤させる効果が大きい

ためと考えられる。 水シャワーでは、回転しているバッ キングロール両端の銭面に需要した水流が鍛ね返って、 銭網な靴や汚れと共に再飛動してしまうので、断紙の発 生を効果的に防止できないものと考えられる。

【の081 バッキングロールの傾面から飛散した値工液粕 は、大概の場合、建工面と反対側の傾面に付着すること が多い、ところが、陸工両と反対側の板面は、建工後直 ちにテンションロール等のロールに接触するから、飛散 した建工液粒が湿滞状態の場合は、万一紙面に付着した 場合でも、乾燥して核となるとなぐ、紙面上に煎散し てしまうので、斯紙の原因にならないものと考えられ る。

【0019】更に、水ミストの粒径についても、各種実験したところ、ザウター平均能が100~400kmの水ミストを連携等することが遅ましいことを認かたまたを明確からには、噴霧される水量が少なくなると同時、水・ストルの体が広範囲に発生し長くなる。したがって、噴霧/ズルをバッキングロールに近接して数多く設置する必要性が生じ、操作性が悪くなるとともに、噴霧/ズルをバッキングロールのは長いているため、バッキングロールのから飛散する建工液のミストが、噴霧/ズルの壊却にをよむいてしまうという現象も発生し易くなるととが分かった。

【0020】逆に、ザウター平均粒径が400μmを大きく 越える水ミストを噴霧した場合には、前述のシャワーリ ングと大差なく、塗工液ミスト又は竣工液符を⇒ーに塞 潤することが難しくなり、断断発生頻度を減少させる効 果が著しく低下するとともに、バッキングロールに衝突 した水ミストが弱ね返って、機細を拍や汚れと共に再限 散してしまうことが判明した。

酸してしまっことが判明した。
「②21 するに、未発明治は、バッキングロール両端の 鏡面だけでなく、両端の外周曲面で、紙と接触しない部 分においても、同様の現実が認められたので、バッキン グロール両端で低と接触しない外周曲面部でも、は、 同様の無細を気が混合ミストを噴霧することにより。さ らに、断紙発生頻度を現象させるすることに成功した。 「②22 また、本発明の気が混合ミストの噴霧効果は、 オンマシンブレードコーターを使用し、1000m/分 以上の高速で塗工する場合に顕著に現れる。オフマシン コークーの場合や1000m/分以下の低速で整工する 場合には、通常の引っ振り強度を持一板の場合。 断紙等 生類質目体が非常と少ないため、本発明の効果の場合。 物が難しくなるが、極度に引っ張り強度の低い低に塗 工規要する場合、本発明の効果の領域をの低い低に塗 工規要する場合、本発明の効果の原数をの低い低に塗 工規要する場合、本発明の効果が顕著に現れることは、 容易に想象を

[0023]

【発明の実施の形態】本発明において、バッキングロール両端の鏡面及び紙と接触しない外周曲面部に噴霧する 微細な水ミストは、経済的観点からもできるだけ少ない 量で済ませることが望ましいことは当然である。噴霧す べき微糊な水ミストの量は、塗工に用いる塗工液の成分 により大きな差が生じる。即ち、塗工液に含まれる顔料 分および樹脂の比率、またそれらの特性により塗工液粕 の発生しやするに差が生じるからである。

【0024】後って、本発明で用いる哨袋機関の構成に関しては、特殊を構造である必要はないが、噴霧する水ミストのサウター平均柱径を、少なくとも100mル~400mルの地間で開意できることと、水ミストの興電量を、お途間で調整できるとことが必要である。また、噴霧速度も調整できるよう、空気供給管と水供給管の両方に流量調整不足は減圧弁成い場をの両方を長傷し、さらに噴霧バターとも開発できるものが遅ましい。

【0025】さらにまた、噴霧位置や噴霧方向や噴霧角度を 自由に開節できる取り付け構造とすることが望ましい。 パッキングロールの外周面両端部の噴霧位置は、塗工す る紙の幅により変化するからである。

【0026】 明霧装置及びその取り付け位置の一例を挙げれ ば、ノスル先端からロール間までの距離は100〜60 のmで、ロールの外周間に鳴響するノズルは、 場方向に移動可能とする。 明報表置の空気圧の基圧 は、5.0 kg/cm²で、減圧弁により、0.5〜 5.0 kg/cm²の範囲で調整可能とし、水田は、ノ 入ル性出に加める水圧を1.0~10.0 kg/cm²の 2 の範囲で調整可能とし、水田は、ノ 、水中はノワール両端外周曲面及び間端の傾面に噴霧で きるよう。それぞれにつき一個所以上取り付ける。

【0027】 本発明において使用するブレードコーターは、 給液方式はロールアプリケート、ファウンテンアプリケート、ショートドウェル型アプリケートのいずれの方式 でも良い、但し、ロールアプリケートが式のプレードコ ーターの場合は、一般にアプリケーターロルとバッキ ングロールとが離れて装置されてもるので、他の2方式 に比べて、捻工液がバッキングロールまで飛散すること が少ないので、本発明は、主として、ファウンテンアプ リケートおよびショートドウェル型アプリケート方式の ブレードコーターに適用すると大きな効果を期待でき

【0028】また、第二方式は早層施工でも二度強り以上の 多層施工でも扱いが、多層施工する場合には、下強り施 工方式を特に限定するものではないが、ゲートローム ーター、ブレードあるいはロッドメタリングサイズプレ スコーター等のフィルムトランスファー方式でも前記同 様を層ブレードコーターでも、801

【0029】 塗工処理する紙は、通常使用される長網フォーマや、ギャップタイプのツインワイヤーフォーマ、長網部の後半部をツインワイヤーで構成するハイブリッドフォーマや甲割あるいは多層で抄紙され、酸性抄紙、中性抄紙、アルカリ性抄紙方式で抄紙した坪

量30~600g/m²のもののいずれであっても良く、ケミカルパルブだけでなくメカニカルパルブや回収 古紙パルブを含む紙を使用しても良い。

【0030】 抄紙された紙は、その後適宜アレス、乾燥された後、必要に応じてデンアンあるいはその誘導体等の水溶性バインダー及び必要に応じ助剤を配合したクリアー並工液を使用して表面サイズ処理されるか、若しくは顔料と接着割等を有する下陸り強工液が強てきれる。

【0031 益工液に使用する顕常には、 重質炭酸カルシウム、 軽質炭酸カルシウム、 カオリン、クレー、デラミネ ・デッドクレー、タルク、サチンホワイト、シリカ、 酸パリウム、 硫酸カルシウム、 酸化亜鉛、 二酸化チタン などの無機原料、 プラスチックピグメントなどの有機原 野等目附いるとかでき、これの原料は必要に応じて 単独または 2種以上混合で使用することができる。

【0052】また、第工液に使用する接着剤は、ラファクス あるいはその他の水性接着剤から必要に応じ、1億あるい は2億以上を選比で使用する。ラテックスとしては、 ステレン・ブタジエン共重合体、メタクリレート・ブタ ジエン共重合体やの共役ジエン系共通合体、テテックス、 アクリル権エステル及び、またはメタクリル権にステルの 面合体まだは共電合体等のビニル系重合体ラテック ス、あるいはこれらを更にカルボキンル等の官能基合有 単量体で変性したものである。

【(0331 ラテックス以外の水柱接着剤としては、例えば 酸化子ンプン、 尿薬リン酸エステル化デンプン等のエス テル化デンプン、 ヒドロキシエチルエーテル化デンプン 等のエーテル化デンプン、 デキストリン、 陽性デンプン 等のデンプン類、 かぜイン、 大豆包含、合成蛋白等の蛋 自質類、 ポリビニルアルコール、 ポリビニルビロリド ン、 無木マレイン酸物節、 メラミン酸原等の合成酸脂素 後着剤、 カルボキシメチルセルロース、 ヒドロキシエチ ルセルロース、 ヒドロキシエチ ルセルロース、 ヒドロキシメチルセルロース等セルロー ス接海株等、 連常の強工用接着所である。 また、 分散 別、 帽格剤、 係の強工用接着である。 また、 分散 別、 帽格剤、 後外別、 清陰剤、 前水化剤等通常の進工紙 用頭料に配合される 希難的剤を使用しても良い。 [0394]

【発明の効果】飛燈した遠江液ミストが、バッキングロールの鏡面及び低と接触しない外周曲面上で整備部化して能工溶剤となり、それが根表面に飛煙すると、能工液
粧が枝となって断能の原因となる。本学明では、バッキングロールに付着した建工液ミストに対して、常時、微 細なホミストを吶騰し、施工流俗の労化を押さえるの で、建工溶剤に退却する断純発生を大幅に減少させることができる。

【図面の簡単な説明】

【図1】 本発明の装置の構造説明図。

【図2】 ロールアプリケート方式プレードコーター の構造説明図


【図3】 ファウンテンアプリケート方式ブレードコ

!(5) 000-107666 (P2000-107666A)


ーター	の構造説明図	E	噴霧ノズル	
【符号	の説明】	M	鏡面	
Α	アプリケーターロール	N	外周曲面	
В	ブレード	- P	塗工液	
C	塗工面	R	バッキングロール	
d	ドライエッジ	S	紙	

【図1】

[図2]



[図3]



フロントページの続き

(72)発明者 平川 昌宏 山口県岩国市飯田町2丁目8番1号 日本 製紙株式会社岩国工場内 F ターム(参考) 4D075 AA01 AC21 AC88 AC92 CA48 DA04 DB18 EA06 4F040 AA22 AA31 AB14 AC01 BA23 CB33 DB06

4L055 BE08 CH12 CH30 EA16 FA22

JP 2000-107666.A

* NOTICES *

JPO and INPIT are not responsible for any damages caused by the use of this translation.

- 1. This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.**** shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

[Claim(s)]

[Claim i]In a coating method of paper which presses a braid against a coating surface and adjusts a coating amount while making a rear face of paper by which coating was carried out in coating liquid contact a backing roll, A coating method of paper spraying water mist of mean particle diameter chosen as both both [either or] which do not contact paper in a both-ends mirror plane or a peripheral surface of a backing roll from a range whose Sauter mean diameters are 100 micrometers - 400 micrometers.

[Claim 2]In a coating apparatus of paper which presses a braid against a coating surface and adjusts a coating amount while making a rear face of paper by which coating was carried out in coating liquid contact a backing roll, A coating apparatus of paper provided with an atomiser which can spray water mist whose Sauter mean diameters are 100 micrometers - 400 micrometers on both both [either or] which do not contact paper in a both-ends mirror plane or a peripheral surface of a backing roll.

[Detailed Description of the Invention]

F00011

Field of the Invention]In the process of carrying out coating of the coating liquid to paper by a braid coating machine, this invention has little slip-of-paper generating, and relates to a braid coating method and a coating apparatus excellent in high-speed-operation nature and productive efficiency.

T00021

[Description of the Prior Art]

It is the feature that the demand in the aiming at advertisement [, such as a throwaway, a catalog, a pamphlet, and direct mail,] and advertisement commercial-in offset printing paper printing field is extended steadily in recent years. Although the commodity value of itself is low, since it is important for these commercial printings that the purpose is attained as an advertisement medium, the good thing of a printing result has been called for by low cost. In order to raise a printing result, while raising the smooth nature of paper, it is necessary to lessen a permeate lump and a blot of printing ink.

[0003]The coated paper which formed thin ****** in the paper face with paints, a synthetic resin, etc. is manufactured for the above-mentioned purpose, and is most used in the printing

field for commerce. The paper which a user's cost cut inclination has also become strong further, and uses it on the other hand is also going to low-grade-izing and a weight saving.

[0004]In order to satisfy the demand of such flourishing lightweight coated paper, by the paper maker, double width of coating equipment and improvement in the speed are advanced in order to aim at more efficient production and cost cut of a product. It is important technical problem to raise productivity, maintaining high quality under such a situation, and examination of a coating method, improvement in the speed of coating, reexamination of coating liquid, etc. are advanced, [0005]As a production system of conventional coated paper, there are paper making, an off-machine method which performs coating at a separate process, and an one machine coating method which performs paper making and coating continuously by one machine, and production with the more efficient one machine coating method is possible. Since the covering nature of stencil paper improves by under coat coating in quality and surface state and printing quality also become good by carrying out coating of the finishing coating liquid after carrying out coating of the under coat coating liquid which includes cheap paints in stencil paper by an one machine, it is in the tendency for multilayer coating-ization to progress also in manufacture of lightweight coated paper.

[0006]Å braid coating machine is mainly used for one machine coating. A braid coating machine mainly has a roll application method and a fountain application method. A roll application method is a coating method which presses a braid against a coating surface and adjusts a coating amount, making it run the rear face of the paper by which coating was carried out with the applicator roll in contact with a backing roll, as shown in drawing 2.

A fountain application method is a coating method which presses a braid against a coating surface and adjusts a coating amount to the surface of the paper it runs in contact with a backing roll while making coating liquid blow off from a nozzle and carrying out coating of the coating liquid to a paper face, as shown in drawing 3.

[0007]However, since the length of a device becomes very long from paper making to finishing coating and desiccation when carrying out coating by an one machine, when it is once generated by the slip of paper (out of paper), in order to refeed sheets, time is taken, and productive efficiency falls greatly. Therefore, the production technology establishment for reducing the occurrence frequency of out of paper as much as possible is needed.

[0008]In the out of paper in a coating machine, except when an excessive tension is added to paper, various factors can be considered. For example, the mirror plane which coating liquid mist disperses and are a coating head and the coating liquid bread circumference, a peripheral surface of a backing roll, and the circular side of both ends, It dries, it adheres to peripheral equipment etc., and also solidified ** disperses in space and it falls, and it serves as a core, out of paper is carried out or out of paper occurs also by mechanical factors, such as a draw by stencil paper defect factors and accelerating originating in *******, dirt, dust, product tampering, etc., and change of a tension.

[0009]Thus, in order to reduce many out-of-paper factors, in the operating site, careful attention is paid, and it washes carefully everywhere at the time of a machine stop, and corresponds. In order to make scattering of the coating liquid mist in a coating machine into the minimum, the backing roll upper part, and an entrance and an exit, Various devices, such as stretching plastic sheeting around coating liquid bread etc., or attaching the rubber sheet for preventing scattering, a vinyl chloride board, a tape, etc. at fountain lip both sides in the case of the braid coating machine of a fountain application method, are also made.

[0010]Nevertheless, in manufacturing lightweight coated paper by an one machine braid coating machine especially at high speed, once out-of-paper occurrence frequency becomes high and out of paper occurs, production loss is large, the time loss spent on passage of sheets also increases, and there is a problem of reducing productive efficiency greatly.

Problem(s) to be Solved by the Invention] In view of the above situations, SUBJECT of this invention has little out-of-paper generating, and it is in providing the braid coating method excellent in productive efficiency, and its coating apparatus.

[0012]

[Means for Solving the Problem]Although it is the main cause that a tension more than intensity of paper starts, out of paper, About a braid coating machine of a fountain application method which is an example of a coating apparatus shown in drawing 3. When a cause of out of paper was pursued wholeheartedly, coating liquid mist dispersed, and it adhered to a coating head, the coating liquid bread circumference, a backing roll, a mirror plane, etc., and also coating **** dried and generated dispersed and fell in space, and also when it became a core of a defect and out of paper occurred, a certain thing became clear plentifully. In drawing 1, although coating liquid injected from a nozzle of a fountain is injected towards a portion except about 5-10-mm dry edge part d from edge of paper, it disperses into the peripheral surface portion N of backing roll R both ends which do not contact dry edge part [of paper] d, and paper. It disperses in the mirror plane M of both ends of the backing roll R. Since it fails to be scratched with the braid B. coating liquid mist which dispersed into the portion N which does not touch paper in peripheral surface portions of dry edge part d and backing roll both ends does not accumulate coating **** so in large quantities. However, it accumulates gradually, dry solidification is carried out, and coating liquid which dispersed in the mirror plane M of a backing roll serves as coating ****** easily.

[0013]Therefore, in this invention, occurrence frequency of out of paper was able to be substantially decreased by spraying detailed water mist on the mirror plane M of the backing roll R continuously, and not drying ** using the atomiser E installed in a position shown in drawing L. Since ** of coating liquid might occur into the portion N which does not always touch paper in a peripheral surface portion of both ends of the backing roll R, when detailed water mist was sprayed also on this portion, it became clear that an effect of decreasing occurrence frequency of out of paper was still larger.

[0014]Hereafter, the feature of this invention is explained in full detail. When this invention person pursues a cause of out of paper wholeheartedly, coating **** which coating liquid mist which mainly adhered to a mirror plane of backing roll both ends dried and produced according to a centrifugal force by rotation of a backing roll, and an air current generated by run of paper. It was admitted that dispersed, fell and adhered to space, it became a core, and out of paper had occurred in comparatively many cases.

[0015]Therefore, in order to flush continuously coating liquid mist adhering to a mirror plane of backing roll both ends and to prevent formation of coating ****, a method of pouring a water shower continuously to ****** of backing roll both ends was tried, but out-of-paper occurrence frequency did not decrease so much.

[0016] Then, as a result of re-examining an out-of-paper factor still more minutely, always making coating liquid mist adhering to a mirror plane into a damp or wet condition has an effect in preventing scattering of ******, and it admitted that out-of-paper occurrence frequency could be reduced. As a result of examining how to make a damp or wet condition hold, a direction of

water mixing mist instead of a water shower which can make particle diameter of water small using high pressure air admitted that an effect was large.

[0017]Although this Reason is not clear, since the effect which moisture permeates homogeneity and carries out humidity to it more to adhering coating liquid mist or coating ***** is large, a direction of more detailed water mist is considered. In a water shower, since waterdrop which collided with a mirror plane of revolving backing roll both ends rebounds and a re-entrainment is carried out with detailed ** and dirt, it is thought that generating of out of paper cannot be prevented effectively.

[0018]Coating **** which dispersed from a mirror plane of a backing roll adheres to a coating surface and space of an opposite hand in many cases, when the most. However, since a coating surface and space of an opposite hand are diffused on space, without drying and becoming a core, even if it should adhere to space when coating **** which dispersed is a damp or wet condition since a roll of a tension roll etc. is promptly contacted after coating, they are considered not to become a cause of out of paper.

[0019]Also about particle diameter of water mist, when experimented [various], it admitted that it was desirable to carry out continuation spraying of the water mist whose Sauter mean diameter is 100-400 micrometers. The water mist itself disperses easily broadly at the same time amount of water sprayed decreases, when water mist whose Sauter mean diameter is more detailed than 100 micrometers is sprayed. Therefore, while the necessity of approaching a backing roll and installing many spraying nozzles arises and operativity worsens, Since a spraying nozzle and a backing roll were close, it turned out that it becomes easy to generate a phenomenon in which mist of coating liquid which disperses from that of a backing roll will plug up an injection tip of a spraying nozzle.

[0020]On the contrary, when a Sauter mean diameter sprays water mist greatly over 400 micrometers. It became clear that it became difficult to carry out humidity of coating liquid mist or the coating **** to the above-mentioned shower ring miformly practically equal, water mist which collided with a backing roll while an effect of decreasing out-of-paper occurrence frequency fell remarkably rallied, and a re entrainment was carried out with detailed ** and dirt. [0021] this invention person in a peripheral surface of not only a mirror plane of backing roll both ends but both ends. Also in a portion which does not contact paper, since same phenomenon was accepted, it succeeded in a thing to do for the phenomenon of the out-of-paper occurrence frequency and to do further by spraying the same detailed water mixing mist as the above also on

a peripheral surface part which does not contact paper at backing roll both ends.

[0022]An one machine braid coating machine is used for the spraying effect of water mixing mist of this invention, and when [1000 m] carrying out coating at the above high speed by /, it shows up notably. In [case / of an off-machine coating machine /, or 1000 m] carrying out coating at the following low speeds by /, in the case of paper with the usual tensile strength, since there is very little out-of-paper occurrence frequency itself, a judgment of existence or nonexistence of an effect of this invention becomes difficult, but. When carrying out coating processing very much at a degree at paper with low tensile strength, it is imagined easily that an effect of this invention shows up notably.

[0023]

[Embodiment of the Invention]As for the detailed water mist sprayed on the peripheral surface part which does not contact the mirror plane of backing roll both ends, and paper, in this invention, it is natural that it is desirable to manage the smallest possible quantity also from an economic viewpoint. A big difference produces the quantity of the detailed water mist which

should be sprayed by the ingredient of the coating liquid used for coating. That is, it is because a difference arises in the ease of generating of coating **** with the pigment content contained in coating liquid, the ratios of resin, and those characteristics.

[0024]Therefore, although it is not necessary to be a special structure about the structure of the atomiser used by this invention, it is required for the Sauter mean diameter of the water mist to spray to be adjusted in the range of 100mmicro-400mmicro at least and to be wide range and to be able to adjust the spray volume of water mist. What possesses a flow control valve, a reducing valve, or its both in both an air feed pipe and a water supply pipe, and can also adjust a spray pattern further is desirable so that spray velocity can also be adjusted.

[0025]It is desirable to make a spray position, a spray direction, and a spray angle into the fitting structure which can be adjusted freely further again. The spray position of the peripheral face both ends of a backing roll is because it changes with the width of the paper which carries out coating.

[0026]If an example of an atomiser and its fixing position is given, the distance from a nozzle tip to a roll side will be 100-600 mm, and the nozzle sprayed on the peripheral face of a roll will presuppose that it is movable to the roll cross direction from roll both ends to the 500-mm inside according to the width of paper. The basis pressure of the pneumatic pressure of an atomiser is 5.0 kg/cm², with a reducing valve, adjustment is made possible in the range of 0.5 - 5.0 kg/cm², and water pressure enables adjustment of the water pressure added to a nozzle delivery in the range of 1.0 - 10.0 kg/cm². One or more fixing positions per each of a nozzle are attached so that it can spray on a backing roll both-ends peripheral surface and the mirror plane of both ends.

[0027]Which method of roll application, fountain application, and short dwelling type application may be [braid coating machine used in this invention] sufficient as a liquid supply method. However, in the case of the braid coating machine of a roll application method, Since it is rare for coating liquid to disperse even to a backing roll compared with other two methods since an applicator roll and a backing roll separate and are generally installed, this invention, A big effect is expectable mainly if it applies to the braid coating machine of fountain application and a short dwelling type application method.

[0028]Although monolayer coating or the multilayer coating more than 2 times coating may be sufficient as a coating method, in carrying out multilayer coating, Although an under coat coating method in particular is not limited, various braid coating machines may be sufficient at film transfer systems, such as gate roll coater, a braid, or a rod metaling size press coating machine, as well as the above.

[0029]The long network former to which normal use of the paper which carries out coating processing is carried out, and gap type twin wire former, Paper making is carried out by the monolayer or a multilayer by the hybrid former and cylinder mold former which constitute the latter half part of a long mesh part from a twin wire, It may be any of the thing of the basis weight 30 which carried out paper making by acid paper making, neutral paper making, and an alkaline paper-making method - 600 g/m², and the paper containing not only a chemical pulp but a mechanical pulp and recovery recycled pulp may be used.

[0030]After being pressed suitably after that and drying the paper by which paper making was carried out, coating of the under coat coating liquid which surface-size processing is carried out using the clear coating liquid which blended the auxiliary agent [, such as starch or its derivative, / a water soluble binder and if needed 1 if needed, or has paints, adhesives, etc. is carried out.

[0031]To the paints used for coating liquid, heavy calcium carbonate, precipitated calcium carbonate, Kaolin, clay, delaminated clay, talc, a satin white, Organic colors, such as inorganic

pigments, such as silica, barium sulfate, calcium sulfate, a zinc oxide, and a titanium dioxide, and a plastic pigment, etc. can be used, and if needed, these paints can be independent or can be used by two or more sort mixing.

[0032]One sort or two sorts or more are chosen and used for the adhesives used for coating liquid if needed from latex or other water borne adhesive. As latex, conjugated diene system copolymer latex, such as a styrene butadiene copolymer and a methacrylate butadiene copolymer, Vinyl-base polymer latex, such as a polymer of acrylic ester and/or methacrylic acid ester or a copolymer, or these are further denaturalized by functional group content monomers, such as carboxyl.

[0033]As water borne adhesive other than latex, for example Esterification starch, such as an oxidized starch and urea phosphorylation starch, Etherification starch, such as hydroxyethyl ether-ized starch, dextrin, Protein, such as starch, such as positive starch, casein, soybean protein, and synthetic protein. Cellulosics, such as synthetic resin glue, such as polyvinyl alcohol, a polyvinyl pyrrolidone, maleic anhydride resin, and melamine resin, carboxymethyl cellulose, hydroxyethyl cellulose, and hydroxymethylcellulose, etc. are the usual adhesives for coating. The various auxiliary agents blended with the usual paints for coated paper, such as a dispersing agent, a thickener, a water retention agent, a defoaming agent, and a water resistance-ized agent, may be used.

[0034]

[Effect of the Invention] If the coating liquid mist which dispersed carries out dry solidification on the peripheral surface which does not contact the mirror plane of a backing roll, and paper, it becomes coating **** and it disperses in a paper face, coating **** will serve as a core and will cause out of paper. In this invention, since detailed water mist is always sprayed and generating of coating **** is pressed down to the coating liquid mist adhering to a backing roll, out-of-paper generating resulting from coating **** can be decreased substantially.

[Brief Description of the Drawings]

[Drawing 1] The structure explanatory view of the device of this invention.

[Drawing 2]The structure explanatory view of a roll application method braid coating machine [Drawing 3]The structure explanatory view of a fountain application method braid coating machine

[Description of Notations]

A Applicator roll B Braid

D Draid

C Coating surface

d Dry edge

E Spraying nozzle

M Mirror plane

N Peripheral surface

P Coating liquid

R Backing roll

S Paper